



Cementone SBR

STRENGTHENS & WATERPROOFS MORTAR MIXES

Date: 22 August 2017

Fact Sheet No.: TDS00320

YOUR SMART ADVANTAGES

- Ideal for bonding and priming
- Improves water, chemical and abrasion resistance
- For waterproof rendering, floor toppings and screeds

USES

Bostik SBR (formerly known as Cementone SBR) is a specially modified Styrene Butadiene Co-polymer Latex for cement and mortar. It toughens, waterproofs and improves chemical and abrasion resistance of renders, screeds and mortar. Bostik SBR is an excellent all round primer and bonding agent especially suitable for external applications.

Bostik SBR can be used for waterproof rendering, flooring screeds and toppings and for bonding renders & suction control.

PRODUCT CHARACTERISTICS

Colour	Milky white
Form	Liquid
Specific Gravity	1.0 approx.
Composition	Modified Styrene Butadiene Co-polymer Latex
Product Code	30812496 5 Litres x 4 30812495 25 Litre
Storage/Shelf Life	Store and transport securely in an upright position. Ensure the cap is fully closed. Store for up to 24 months from date of manufacture in original, unopened packaging under

cool, dry conditions within the temperature range of +5°C to +25°C and out of direct sunlight. Protect from frost.

TYPICAL PERFORMANCE DATA (Approx.)

Mix Ratios	Mix Ratio is dependent on application being carried out. See the relevant application section for details.
------------	--

DIRECTIONS FOR USE

IMPORTANT: Before using Bostik SBR refer to the relevant Health & Safety Data Sheet, available at www.bostik.co.uk.

PREPARATION

1. Wear gloves and suitable eye/face protection.
2. Ensure surfaces are sound, clean, dry and free from grease, oil, paint, laitance and loose materials.
3. Key surface by scabbling, vacuum grit blasting or planing.
4. Ensure the working temperature is above 5°C.
5. For all applications, dampen porous surfaces before applying the appropriate Bostik SBR Bonding slurry.
6. Sands must be well graded, clean and meet the appropriate British Standards.
7. Aggregates must be dust-free.

APPLICATION

This product has been designed to work with Portland cement: CEM I and Portland-fly ash cement: CEM II/B-V. For other types of cement e.g. Portland-limestone CEM II / A-LL it is recommended that a small trial is carried out to ascertain the optimum mix ratios as these cement types and sand can vary.

IMPORTANT: Do not use in concrete which is structural i.e. load bearing, reinforced, pre-stressed or steam cured. Work should not be carried out at temperatures below

+5°C or when temperatures are expected to fall below this. Ensure materials and procedures comply with the appropriate British Standards. Do not exceed ratios stated. Do not overmix or over-trowel. Do not use with other admixtures. Do not add to lime based mixes. Do not use with high alumina, sulphate resisting or extra rapid hardening cement. When rendering protect render from drying too quickly. This product is not vapour proof, therefore structures must incorporate a suitable damp-proof membrane. Ensure the substrate is strong enough to support the weight of any screeds or render being applied.

Bonding Slurry: For screeds, toppings, renders and coatings.

8. Mix 2 parts cement to 1 part Bostik SBR by volume to a stiff brushable consistency. Do not add water.
9. Apply evenly to dampened surface to a nominal thickness of between 1mm and 2mm.
10. Apply screed, topping, render or coating while the slurry is tacky (this normally takes 20 to 40 minutes).

Please note the following recommendations are for guidance only and do not constitute a specification.

Floor Toppings and Screeds:

11. Mix and apply the following mix designs dependent on thickness required:

For thickness <12mm

By Weight		By Volume	
Cement	25 kg	Cement	1 part
Sand	62.5 kg	Sand	2 parts
Bostik SBR	5 litres	SBR : Water = 1 : 1	
Water *	5 litres		

For thickness >12mm

By Weight		By Volume	
Cement	25 kg	Cement	1 part
Sand	75 kg	Sand	2.5 parts
Bostik SBR	5 litres	SBR : Water = 1 : 1	
Water *	5 litres		

* 5 litres of water is recommended for dry sand mixes. If sharp washed sand is wet, reduce water quantity accordingly.

12. Keep mix just wet enough to obtain good compaction. Finish quickly with a steel trowel.

External Waterproof Renders Above Ground:

13. Apply bonding slurry, stipple to provide a key and allow to dry.
14. Then apply second bonding slurry coat at right angles to the first, stipple to provide a key.
15. Apply render mix while second slurry coat is still tacky.

Render Coat Mix	
Cement	25 kg
Sharp washed sand	75 kg
Bostik SBR	5 litres
Water	5 litres

16. 5 litres of water is recommended for dry sand mixes. Reduce quantity accordingly if sand is wet.
17. Apply 2 - 6mm render coats allowing no more than 8 hours between coats. If longer, apply a bonding slurry between coats.
18. Prevent from drying out during the first 48 hours by covering with polythene or mist spraying with water when initially firm.

OTHER APPLICATIONS

Suction Control:

19. Mix 1 part Bostik SBR to 4 parts water. Brush on to surface and allow to dry.

CLEANING

20. Clean tools and equipment immediately after use with water. Dried product is difficult to remove

PRECAUTIONS IN USE

This product has been designed to work with Portland cement: CEM I and Portland-fly ash cement: CEM II/B-V. For other types of cement e.g. Portland-limestone CEM II / A-LL it is recommended that a small trial is carried out to ascertain the optimum mix ratios as these cement types and sand can vary.

IMPORTANT: Do not use in concrete which is structural i.e. load bearing, reinforced, pre-stressed or steam cured. Work should not be carried out at temperatures below +5°C or when temperatures are expected to fall below this. Ensure materials and procedures comply with the appropriate British Standards. Do not exceed ratios stated. Do not overmix or over-trowel. Do not use with other admixtures. Do not add to lime based mixes. Do not use with high alumina, sulphate resisting or extra rapid hardening cement. When rendering protect render from drying too quickly. This product is not vapour proof, therefore structures must incorporate a suitable damp-proof membrane. Ensure the substrate is strong enough to support the weight of any screeds or render being applied.

For any application not covered please contact Technical Services on +44 (0)1785 272625 or visit www.bostik.co.uk for advice.

Recommendations and suggestions are for guidance only, since conditions of use are completely beyond our control.

For health and safety instruction, first aid measures and spillage and disposal instructions, see separate Health and Safety Data sheet for Bostik SBR, available at www.bostik.co.uk.

BOSTIK HOTLINE

Smart help +44 (0) 1785 272625



This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company which may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, nor its liability for fraud, or fraudulent misrepresentation, nor any other liability which cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use which is inappropriate or use which is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company.

Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products, and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top right hand corner on the front of this document.

Sales	Tel: 0844 371 1192	Fax: 01785 241818	customer.service@bostik.com
Technical Advice	Tel: 0844 371 1197	Fax: 01785 272867	technical.service@bostik.com
Technical Data & COSHH (MSDS) Data Sheets	Tel: 01785 272625	Fax: 01785 212962	stafford.gatehouse@bostik.com