

ORGANIC

DESIGNED by NATURE and **KNAUF**

Organic is an acoustic panel with a very good performance. Organic can be adapted to all aesthetic and acoustic requirements for ceilings and wall finishes, both inside and out.

- α_w max. 0.60
- Attractive aesthetic finish
- Available in various different dimensions and colours
- Available with 8 different edge finishes



SPECIFICATIONS

Thickness (mm)	Length (mm)	Width (mm)	Standard fibre width	Standard Edge finish	Panels / pallet	m ² / pallet
15	600 / 1200	600	1.0 mm	SK-04	126 / 63	45.36
25	600 / 1200	600	1.0 mm	SK-04	84 / 42	30.24
35	600 / 1200	600	1.0 mm	SK-04	56 / 28	20.16

Options

Organic Authentic	2.0 mm
Length	2000
Fire classification	A2-s1,d0

CERTIFICATIONS





SOUND ABSORPTION

Panel type	α_P						Average			Report number
	125	250	500	1000	2000	4000	α_w	NRC	SAA	
Direct mounting										
Organic 25	0.10	0.20	0.30	0.55	0.85	0.70	0.40	0.50	0.44	AC15-26055621
Organic 35	0.10	0.25	0.45	0.80	0.90	0.85	0.50	0.60	0.56	AC15-26055621
Plenum 200 mm										
Organic 15	0.20	0.45	0.35	0.50	0.60	0.60	0.50	0.50	0.43	AC15-26055621
Organic 25	0.25	0.55	0.55	0.50	0.65	0.80	0.55	0.60	0.52	AC15-26055621
Organic Authentic 25	0.25	0.60	0.55	0.45	0.60	0.80	0.55	0.55	0.50	AC15-26055621
Organic 35	0.30	0.65	0.60	0.55	0.75	0.90	0.60	0.65	0.58	AC15-26055621
Organic Authentic 35	0.40	0.70	0.60	0.55	0.80	0.90	0.60	0.70	0.62	AC15-26055621
Plenum 200 mm + 60 mm Glass wool insulation										
Organic 25	0.60	1.00	1.00	0.95	0.85	1.00	0.95	0.96	0.88	AC15-26055621
Organic Authentic 25	0.60	0.90	0.95	0.85	0.75	0.95	0.85	0.90	0.80	AC15-26055621
Organic 35	0.60	1.00	1.00	0.95	0.95	1.00	0.95	1.00	0.91	AC15-26055621
Organic Authentic 35	0.70	0.85	0.80	0.75	0.90	1.00	0.80	0.85	0.76	AC15-26055621

TECHNICAL SPECIFICATIONS

Properties	Symbol	Description	Unit	Standard		
Fire classification	-	B-s1,d0 / A2-s1,d0 (Optional)	-	EN 13501-1		
Thermal conductivity coefficient	λ	B-s1,d0: 0.08 / A2-s1,d0: 0.09	[W/mK]	EN 12667		
Thermal resistance	R_D	15	25	35	[m ² K/W]	EN 12667
		0.15	0.25	0.40		
Weight	-	8.0	11.0	14.0	kg/m ²	-
Light reflectance value	LRV	Table 'light reflectance values' (www.organic.design)	-	BS8493		
CE Code	WW-EN13168-T1 / EN 13964:2014					
DoP code	4091_ORGANIC					
Wood wool standard	EN 13168:2012+A1 / EN 13964:2014					



Do you want more information? Please contact us

Knauf Insulation B.V.

+ 31 (0)162 - 42 12 45

customerservice.nl@knaufinsulation.com

www.organic.design

Extreme caution was observed when putting together and processing the information, texts and illustrations in this document. Nevertheless, errors cannot quite be ruled out. The publisher and editors cannot assume legal responsibility or any liability whatever for incorrect information and the consequences thereof.

V1-EN 12/2020